



National Academy of Opticianry

Continuing Education Course

Approved by the American Board of Opticianry

Lens Materials and Design

National Academy of Opticianry

8401 Corporate Drive #605

Landover, MD 20785

800-229-4828 phone

301-577-3880 fax

www.nao.org

Copyright© 2020 by the National Academy of Opticianry. All rights reserved.
No part of this text may be reproduced without permission in writing from the publisher.

National Academy of Opticianry

PREFACE:

This continuing education course was prepared under the auspices of the National Academy of Opticianry and is designed to be convenient, cost effective and practical for the Optician.

The skills and knowledge required to practice the profession of Opticianry will continue to change in the future as advances in technology are applied to the eye care specialty. Higher rates of obsolescence will result in an increased tempo of change as well as knowledge to meet these changes. The National Academy of Opticianry recognizes the need to provide a Continuing Education Program for all Opticians. This course has been developed as a part of the overall program to enable Opticians to develop and improve their technical knowledge and skills in their chosen profession.

The National Academy of Opticianry

INSTRUCTIONS:

Read and study the material. After you feel that you understand the material thoroughly, take the test following the instructions given at the beginning of the test. Upon completion of the test, mail the answer sheet to the National Academy of Opticianry, 8401 Corporate Drive, Suite 605, Landover, Maryland 20785 or fax it to 301-577-3880. Be sure you complete the ABO – NCLE evaluation form on the answer sheet. Please allow two weeks for scoring and test results.

CREDITS:

The American Board of Opticianry has approved this course for one (1) Continuing Education Credit toward certification renewal. To earn this credit, you must achieve a grade of 80% or higher on the test. The Academy will notify all test takers of their score and mail the credit certificate to those who pass. You must mail the appropriate section of the credit certificate to the ABO and/or your state licensing board to renew your certification/licensure. One portion is to be retained for your records.

AUTHOR:

Diane F. Drake, LDO, ABOM, NCLEM, FNAO

INTENDED AUDIENCE:

This course is intended for opticians of all levels.

COURSE DESCRIPTION:

This course will explain basic ophthalmic lens materials and designs. Information will include index of refraction, impact resistance, lens material classifications, and Abbe value.

OBJECTIVES:

At the completion of this course, the student should be able to:

- Understand different ophthalmic lens materials
- Explain the classifications of lens materials
- Explain the difference in lens design, spherical vs. aspheric
- List advantages and disadvantages of different materials

Lens Materials and Design

Diane F. Drake, LDO, ABOM, NCLEM, FNAO

There has been a literal explosion of newer high-tech lenses in the marketplace over the last few years. It is no longer just a case of "**Do you want glass or plastic lenses?**" Before you can really understand what the major differences are between the old and new materials you will have to familiarize yourself with a few terms.

More lens designs and materials have been introduced into the market during the last five years than in the previous 60. Keeping that in mind, as you study this document, newer technologically advanced lens designs and materials have already been introduced and more will continue to be introduced.

This course will present some manufacturers' names and trade names. It is not the intent of these authors to attempt in any manner to sway you toward one manufacturer or another. It is our intent to simply present various options that may be available by a number of companies.

This course will NOT present digitally designed lenses as that will be another topic.

Very Brief Timeline of Lens Design₁ – Information from System for Ophthalmic Dispensing – Third Edition

- *1200 – 1800: Flat lenses*
 - *Not actually flat, but shaped more like a lentil. Central vision was OK, but dramatically digressed in the periphery*
- *1800's – Periscopic Lenses*
 - *Change in design utilizing a -1.25D back surface power*
- *Beginning around 1890's – Six-base meniscus lenses*
 - *Because of the minus curve on the back surface, vision was dramatically improved.*
- *Early 1900's – Correct Curve Lenses*
 - *Introduced by Carl Zeiss Company*
 - *Lenses were designed to approximate the rotation of the eye and were designed to correct for oblique astigmatism found in the periphery of the lenses.*
- *Early 1900's – Aspheric lenses*
 - *Originally introduced for use in very high plus "cataract" style lenses*
 - *Became more used in lower powers in late 20th century in plus as well as minus*
 - *Primarily as a result of more material availability*
- *Late 1990's – Atoric lenses*
 - *Aspheric design on both sides of the lens*
 - *Used to increase the field of view due to reducing optical aberrations in both principal meridians*

Lens Materials

As an optician, there are a number of factors you will be considering every time you select or recommend a lens material for your patients. While many ECPs feel that the patient's primary concern is how thick their lenses will be, that may not be the case in every situation. Therefore, one must determine which is the most important based upon the intended usage of the eyewear. These factors include the following:

- Index of Refraction
 - How much does it bend light?
- Abbe Value
 - What are the optical properties of the material?
- Specific Gravity
 - What are the lenses going to weigh?
- Impact Resistance
 - How safe are these lenses?

Now, let's go a little more in-depth with each of these.

Refractive Index/Index of Refraction

Index of refraction is the term most eye care professionals are familiar with. The higher the index of refraction the more the material will bend light rays. Therefore, a higher index lens will require less material and be thinner.

The terms refractive index and index of refraction are considered interchangeable. As previously discussed in this program, the index of refraction is a numerical expression comparing the speed of light in a transparent medium to the speed of light in air (vacuum). The formula to determine index of refraction is:

$$\text{Index of refraction (n) of the substance} = \frac{\text{Speed of light in air}}{\text{Speed of light in substance}}$$

For instance, we know that the speed of light in air is roughly 186,000 miles per second. The speed of light through crown glass which is denser than air is 122,127 mps, so we can now determine the index of refraction of the lens made of crown glass.

$$n = \frac{186,000}{122,127} = 1.523$$

So, let's say you know the index of refraction of a material is 1.498. What is the speed of light through the material? Reverse the formula.


$$S = \frac{186,000}{1.498} = 124,165 \text{ MPS}$$

The following is a table with some common index of refraction. However, we do not use these for ophthalmic lenses.

Material	Index of Refraction
Air	1.00
Ice	1.31
Water	1.33
Diamond	2.41

You will notice in the chart above that while water and ice are the same basic material, when water freezes and becomes ice, it also expands; therefore, the molecules are further apart and the specific gravity also changes. Ice weighs less and will float in water. It also has a lower index of refraction; therefore, will not bend light as much as water.


Refraction is responsible for image formation by lenses and the eye.



With the index of refraction of air being 1.00, we can safely assume that any transparent substance with a higher number will also be denser than air, therefore slowing the speed of light. When light reaches a denser material it also gets refracted more. Another hard rule to remember is that the higher the index of refraction, the thinner the lens as compared to lenses of a lower refractive index.

An increased index of refraction can have a dramatic difference on the final thickness, weight, and profile of a lens. The reduced thickness translates into a lighter and more comfortable product, too.

As the index of refraction increases, a lens of a given prescription and diameter needs less curvature and thickness to produce the same power. For plus lenses, this translates into thinner centers; for minus lenses, it means thinner edges.




Abbe Number

Ernest Abbe, working with Carl Zeiss and Otto Schott, developed a mathematical formula to determine the amount of chromatic aberration a lens material will produce. The higher the number, the better the optics of the material due to the decrease of the amount of chromatic aberration caused by light passing through a refractive medium and breaking down into its component colors (dispersion).

The Abbe value of lens material (sometimes referred to as Nu value or V number) is the reciprocal of the dispersive power of the lens. Dispersive power being the characteristic of a lens that breaks up white light into its component colors, a rainbow. Abbe numbers range from 20 - 60. The higher the Abbe number, the less chromatic dispersion occurs.

When white light (e.g., sunlight) is refracted, it breaks down into a rainbow. This is referred to as “dispersion,” which results in a chromatic aberration. Abbe value is the measure of a material’s characteristic of breaking light into its component colors. It has been a constant concern with high index lens materials. If the color aberration is significant enough, the lens wearer will likely see some reduction in vision quality and possibly colored ghost images around objects.

The index of refraction of a material varies with wavelengths; different wavelengths of light are focused at different focal points by a lens.



All lenses will have chromatic aberration. Here is a plus lens. Hyperopes usually will not complain about the “rainbows” as they travel along the optical axis of the lens.



Myopes generally will be very sensitive to the “rainbows” around the edges. The higher the minus, the more they will notice. As lens size will have an effect also, large eyesize equates to more color. Abbe needs to be at the forefront of your lens material choice.



ABBE Values of Some Common Lens Materials

Material	Manufacturer	ABBE Value
Crown	Many	59
CR-39	Many	58
Trivex®	Many	43-45
Polycarbonate	Many	29-36
1.60	Many	32-42
1.67	Many	31-32

Specific Gravity

Specific gravity is a weight issue. The higher the specific gravity the heavier the lens will be. We need to balance the thinness of a high index material with its weight. It is the given comparison of a lens material to an equal volume of water. Specific gravity is independent of index of refraction and Abbe value.

This is a measurement of physical density, not an optical characteristic. The weight of the material is measured in grams per cubic centimeter. For our purposes, the lower the specific

gravity of a lens material the lighter the lens will be. We all know that lightweight is a very highly desirable patient benefit.

Weight of a given volume of a substance

Weight of equal volume of water

Weights of high index materials vary considerably, with glass products leading the list as the heaviest. Thinner doesn't necessarily mean lighter weight. Some high index products have a higher specific gravity than others. An aspheric lens design is a good way to make lenses thinner, which also makes them lighter.

Material	Manufacturer	Specific Gravity
Trivex®	Many	1.11g/cm ³
Polycarbonate	Many	1.21g/cm ³
CR-39	Many	1.34g/cm ³
1.60	Many	1.22g/cm ³
1.67	Many	1.35g-1.36g/cm ³
Crown Glass	Many	2.62g/cm ³

Impact Resistance

Safety is a major concern to ECPs and to patients. Impact resistance testing will be discussed more in-depth later in this program.

The two additional lens safety tests are the High-Velocity Impact Test and the High Mass Impact Test.

High-Velocity Impact Test

One of the impact resistance tests is called the High-Velocity Impact Test. Lens materials that pass this test can withstand an impact from a 1/4-inch round pellet fired at 150 feet per second and not break. This is the level of impact resistance required of some safety eyeglasses. That substantial impact resistance is a huge selling point at the dispensing table, no matter how high or low the patient's prescription may be.

Though it seems the opposite may be expected, high impact requirements allow the lenses to be thinner than basic-impact lenses. The thickness requirement for high-impact safety lenses is a minimum of 2.0 mm for both Rx and plano. AR coatings generally reduce the impact resistance of the same lens in the uncoated state. The reduction will depend on the material and the type of coating.

High Mass Impact Test

Polycarbonate and Trivex® will also pass the High Mass Impact Test. The High Mass Impact Test uses a 500g (17.6 oz.) pointed projectile dropped from a height of 127cm (50 in.)

Formerly, dress ophthalmic lenses had a minimum thickness requirement of 2.0 mm. Now there is no thickness requirement, regardless of lens material. Impact resistance requirements are performance-based. If a lens thinner than 2.0 can pass the standard drop ball test, (meaning it doesn't break) which is having a 5/8 inch steel ball, weighing .56 ounces from a height of 50 inches, the lens material is considered acceptably safe for dress use. All lens materials today can meet the current requirements for dress lenses.

Classifying Lens Materials

Most ECPs recognize four material index categories—low, mid, high, and ultra-high. There is no official standard that subdivides these materials, but the optical industry generally follows this breakdown:

- Low index: <1.53
- Mid index: 1.53 to 1.58
- High index: 1.59 to 1.66
- Ultra-high or super-high index: >1.66

ECPs are moving to higher index lenses. The optical advantage of flatter base curves helps the lens shed some thickness. Additionally, thinner lenses look more attractive and are lighter in weight, making them more comfortable to wear.

Lens Materials

We will be touching on some of the highlights of the different lenses here.

CR-39

The most commonly used plastic lens material for years was CR-39. It was first developed as a replacement for glass lenses during World War II. It still has 55% of the world market at age 60. The patent was awarded to Muskat and Strain of Pittsburgh Plate Glass Company (now named PPG) in 1946. CR-39 is available in all lens styles and from multiple manufactures. The basic monomer comes from PPG, and then each company adds its own materials to create their lenses. Advantages include lightweight, good optical properties, and tinting well. The disadvantages of CR-39 are that it is the thickest material and scratches more easily than glass.

Glass Lenses

While today, only 5% of lenses are made of various types of glass, for educational purposes, the information will be presented.

Crown Glass is the most commonly used clear glass for ophthalmic lenses. In general, glass is the most durable material used for lenses. Crown glass is used mainly for single vision lenses and the distance carrier for most glass bifocals and trifocals. It has an index of refraction of 1.523, and an Abbe value of 59. It is approximately 4% thinner than CR-39 resin lenses, and is 40% heavier than polycarbonate lenses, and is slightly lighter than high index glass. It blocks out about 10% of UV light.

Flint Glass uses lead oxides in its chemical make up to increase its index of refraction to approximately 1.58 to 1.69. Its Abbe value ranges from 30 to 40. This material is relatively soft, displays a brilliant luster, and has chromatic aberration. Although it was used in the past as a single vision alternative for higher Rx lenses, its use today is often limited to segments for some fused bifocals.

Barium Glass is a lens that uses barium as its main ingredient. This gives it an index of refraction from 1.51 to 1.616 and an Abbe value of 55 to 59. This allowed this material to be used in the bifocal segment in the Nokrome series of fused bifocals. The high Abbe value allowed those using the bifocal to experience no color dispersion when reading.

Highlite 1.7 Glass, here the name identifies the index of refraction. Its Abbe value is 32. This lens is about 25% thinner than CR-39 and blocks approximately 18% of UV light.

Thindex 1.8 Glass, again the name gives its index of refraction. This lens uses a titanium oxide in its ingredients. It is about 35% thinner than CR-39, 18% heavier than crown glass, and offers 18% protection from UV light.

The advantages of glass lenses include optical clarity, resistance to scratches, and it is the least susceptible to chemicals. The disadvantages include that it is the heaviest material and it is less impact-resistant than other materials

At the beginning of this course, we said that the higher the index, the thinner the lenses. Well, with glass, the higher the index, the heavier the lenses. Glass is not the material of choice when weight is a factor. But even in today's market, glass still has a place although only about 5%.

Trivex®

Originally developed as “visual armor” for the military, PPG Industries adapted the plastics technology in 2001 for use in the ophthalmic industry and called it Trivex® lens material because of its unique tri-performance properties. An entirely new category, Trivex® material is the first to offer the combination of excellent optics, strength characteristics, and ultra-lightweight qualities in a single lens material. Another advantage of Trivex® is ultraviolet light protection inherent in the material.

Tribrid

Tribrid is a new lens material from PPG that uses a hybrid technology to combine the qualities of Trivex material with those of traditional high-index materials. Tribrid material's index of

refraction is 1.60 and it is the third-lightest lens material behind Trivex material and polycarbonate. It is also clear with an Abbe value of 41. Tribrid is much stronger than most lens materials but not as strong as Trivex or polycarbonate.

Polycarbonate Lenses

Today, polycarbonate accounts for approximately 65% of all lenses sold in the US. Polycarbonate lenses were first developed by a company named Gentex. Polycarbonate is a thermoplastic which means it is moldable under sufficient heat. In the 1950's it was marketed under the name Lexan and due to its extraordinary resistance to impact was originally manufactured for safety devices. In 1978 the first single vision lens appeared for industrial usage. It was two years later that the first dress wear lenses appeared.

Most advances in the quality of polycarbonate are thanks to the music and DVD industry. Not all polycarbonate is manufactured using the same methods. The elimination of birefringence improves the optics of the lenses. Birefringence is the optical property of a lens material that causes the polarization of light to travel at different speeds causing dispersion. Advantages include that polycarbonate is the most impact-resistant lens on the market. it is lightweight, has a 1.586 index of refraction and built-in UV protection. Its only disadvantage is the low Abbe value. Because it is considered the softest lens material, it requires a hard coating to prevent scratching

High Index and Ultra High Index Lens Materials

You will probably find that high index lenses will have benefits for those approximately 20% of your patients that have higher power prescriptions. They should be considered for your patients looking for lenses with the following advantages:

- Are up to 50% thinner and 50% lighter than a regular resin lenses
- Offer superior optics, when compared to traditional polycarbonate
- Have flatter front curves for improved cosmetics and ease of insertion in frames

Tensile Strength

Another consideration for lens material selection, especially in rimless styles and drill mounts, is the tensile strength of a material. Tensile strength measures the force required to pull a material apart or break.

Lens Designs


Now that you have selected the appropriate lens material, you now have to determine the appropriate lens design. Lens designs include spherical, cylindrical, aspheric, and atoric.

Spherical

A spherical lens surface design is one in which the surface has the same power in all meridians. It also has the same curvature from the center to the edge. The spherical surface may be on the

front, the back, or on both surfaces. An example of a spherical lens surface design is illustrated below.


Spherical Surface



Cylindrical


A cylindrical lens surface design is one that will have two distinct curves on a surface. Historically a cylindrical surface could occur on either the front or the back surface. Today, the cylindrical surfaces are found on the back. In cylindrical lenses, there are two curves of different power. They do not vary from the center of the lens to the edge of the lens in their respective meridians. A spectacle lens will not have a TRUE cylinder surface because in one of the two principal meridians the curve is flat. A spectacle lens actually has a toric cylindrical surface. An example of a cylindrical lens surface design is illustrated below.

Toric Surface



Aspheric

An aspheric lens surface design is one in which the curvature of the lens gradually flattens as you move from the geometrical center out to the edge of the lens. An aspheric design offers a better looking profile to higher power lenses and reduces magnification, especially high power plus. The overall lens profile will be flatter.



Atoric

An atoric lens design is a lens that has an aspheric front curve and an atoric back curve. Atoric lens designs are used in many free-form lens designs. It is also a design used for lenses in wrap frames to improve the peripheral optics in a lens. Atoric lenses can improve the optics in both the sphere and cylinder components of a prescription.

National Academy of Opticianry

8401 Corporate Drive #605

Landover, MD 20785

800-229-4828 phone

301-577-3880 fax

www.nao.org

Copyright© 2020 by the National Academy of Opticianry. All rights reserved.
No part of this text may be reproduced without permission in writing from the publisher